



# RAVATHANE<sup>®</sup>

## Technical Data Sheet

### Ravathane<sup>®</sup> 210 D65 M25

**Description:** Thermoplastic polyurethane based on polyether having strong resilience and tear resistance, excellent abrasion resistance, excellent resistance to hydrolysis failure and microbial attack, good stability towards solvents and light.

**Application:** Injection molding.

**Features:** matting effect.

### Typical Properties

PROPERTIES	TEST METHOD	UNITS	VALUES
Hardness	ISO 868	Shore D	65
Density	ISO 1183-1 A	g/cm <sup>3</sup>	
Tensile stress at:			1,10
-100% elongation	ISO 37	MPa	15
-300% elongation	ISO 37	MPa	25
Tensile strength at break	ISO 37	MPa	35
Elongation at break	ISO 37	%	400
Tear strength	ISO 34-1 B/b	N/mm	150
Abrasion resistance	ISO 4649	mm <sup>3</sup>	60

Properties have been tested on injection molded plaques conditioned 24 hours at room temperature before testing.

### Application Guideline (Injection Molding)

Nozzle (°C)	Metering (°C)	Compression (°C)	Feed (°C)
210-230	215-235	215-235	210-230

Before processing, the pellets have to be dried at 80-90°C for 2-4 hours. Maximum moisture content should be below 0.02%.