



ENFLEX VU-420-40A

ENFLEX-V

Alcohol	Excellent
Olive Oil	Fair
Sulphuric Acid	Good
Detergent	Good

Drying Condition

Drying Time(hr)	2
Drying Temperature(°C)	80-90

Molding Condition (°C)

1st Zone (hopper)(°C)	170-180
2nd Zone(°C)	180-190
3rd Zone(°C)	190-200
Nozzle(°C)	200-210
Melt Temperature(°C)	210-220
Mold Temperature(°C)	10-50
Max Allowable Melt Temperature(°C)	250 C

Extrusion Condition (°C)

Feed Zone Temperature (°C)	170 - 190
Compression Zone Temperature (°C)	180 - 195
Melting Zone Temperature (°C)	195 - 205
Extruder Head Temperature (°C)	200 - 210
Die Temperature (°C)	200 - 220

