



**ENFLEX VU-424-65A**

**ENFLEX-V**

**Product Description :** This polyolefin based thermoplastic elastomer (TPE-V) compound is a dynamically vulcanized EPDM/PP blend with improved flow behaviour. ENFLEX® series are completely recyclable and can be processed with conventional thermoplastics machinery

**Additive Packages :** T / Heat and UV stabilizer  
/

**Key Features :** Excellent ozone, UV and weathering resistance  
Rubberlike elasticity in a wide temperature range  
Easy processing  
Colorable with proper MB (PE, PP, etc. based)

**Process Method :** Extrusion, coextrusion, sheet extrusion, injection/multi injection molding

**Uses :** Automotive, construction, home appliances, wire&cable, industrial applications

	Value	Unit	Standard
<b>Physical</b>			
Hardness	65	SHORE A	ISO 868 (3 second)
Density	0,98	gr / cm3	ISO 1183 1-A
<b>Mechanical</b>			
100% Modulus	1,9	Mpa	ISO 37(S1,500 mm/min)
300% Modulus	3	Mpa	ISO 37(S1,500 mm/min)
Tensile Strength At Break	7,9	Mpa	ISO 37(S1,500 mm/min)
Elongation at Break	660	%	ISO 37(S1,500 mm/min)
Tear Strength (Perpendicular to flow)	22,8	N/mm	ISO 34-1 Method B
<b>Aging</b>			
Compression Set (72h/23°C)	28	%	ISO 815
Compression Set (22h/70°C)	39	%	ISO 815
Compression Set (22h/100°C)	53	%	ISO 815
<b>Environmental Resistance</b>			
Ozone	Excellent		
Water	Excellent		



Ravago Petrokimya Uretim A.S.



**ENFLEX VU-424-65A**

**ENFLEX-V**

---

Alcohol	Excellent
Olive Oil	Fair
Sulphuric Acid	Good
Detergent	Good

---

**Drying Condition**

Drying Time(hr)	2
Drying Temperature(°C)	80-90

---

**Molding Condition (°C)**

1st Zone (hopper)(°C)	170-180
2nd Zone(°C)	180-190
3rd Zone(°C)	190-200
Nozzle(°C)	200-210
Melt Temperature(°C)	210-220
Mold Temperature(°C)	10-50
Max Allowable Melt Temperature(°C)	250 C

---

**Extrusion Condition (°C)**

Feed Zone Temperature (°C)	170 - 190
Compression Zone Temperature (°C)	180 - 195
Melting Zone Temperature (°C)	195 - 205
Extruder Head Temperature (°C)	200 - 210
Die Temperature (°C)	200 - 220

