



# EZPRENE® VU-320-45A-T

## Ravago Manufacturing Turkey - Thermoplastic Vulcanizate

### General Information

#### Product Description

This polyolefin based non-hygroscopic thermoplastic elastomer (TPE-V) compound is a high performance, dynamically vulcanized EPDM/PP blend with improved flow behaviour. EZPRENE® series are completely recyclable and can be processed with conventional thermoplastics machinery

#### Additive Packages :

T / Heat and UV stabilizer

#### Key Features :

Non hygroscopic, no pre-drying

Excellent ozone, UV and weathering resistance

Rubberlike elasticity in a wide temperature range and low compression set

Easy processing, faster cycle time over conventional TPVs

Easy colorability with proper MB (PE, PP, etc.)

#### Process Method :

Extrusion, coextrusion, blow molding, sheet extrusion, injection/multi injection molding

#### Uses :

Automotive, construction, home appliances, wire&cable, industrial applications

#### General

Material Status	• Commercial: Active		
Availability	• Europe		
Additive	• Heat Stabilizer	• UV Stabilizer	
Features	<ul style="list-style-type: none"> <li>• Chemical Resistant</li> <li>• Fast Molding Cycle</li> <li>• Good Colorability</li> <li>• Good Flow</li> <li>• Good Processability</li> </ul>	<ul style="list-style-type: none"> <li>• Good Weather Resistance</li> <li>• Heat Stabilized</li> <li>• High Elasticity</li> <li>• Low Compression Set</li> <li>• Low to No Water Absorption</li> </ul>	<ul style="list-style-type: none"> <li>• Ozone Resistant</li> <li>• Recyclable Material</li> <li>• UV Resistant</li> <li>• UV Stabilized</li> </ul>
Uses	<ul style="list-style-type: none"> <li>• Appliances</li> <li>• Automotive Applications</li> </ul>	<ul style="list-style-type: none"> <li>• Construction Applications</li> <li>• Industrial Applications</li> </ul>	<ul style="list-style-type: none"> <li>• Wire &amp; Cable Applications</li> </ul>
Processing Method	<ul style="list-style-type: none"> <li>• Blow Molding</li> <li>• Coextrusion</li> </ul>	<ul style="list-style-type: none"> <li>• Extrusion</li> <li>• Injection Molding</li> </ul>	<ul style="list-style-type: none"> <li>• Multi Injection Molding</li> <li>• Sheet Extrusion</li> </ul>

### Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density	0.970	g/cm <sup>3</sup>	ISO 1183/A

# EZPRENE® VU-320-45A-T

## Ravago Manufacturing Turkey - Thermoplastic Vulcanizate

<b>Elastomers</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Tensile Stress (100% Strain)	1.30	MPa	ISO 37
Tensile Stress (300% Strain)	2.70	MPa	ISO 37
Tensile Stress (Break)	5.10	MPa	ISO 37
Tensile Elongation (Break)	500	%	ISO 37
Tear Strength - Across Flow	24.0	kN/m	ISO 34-1
Compression Set			ASTM D395B
23°C, 72 hr	19	%	
70°C, 22 hr	23	%	
<b>Hardness</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Shore Hardness (Shore A, 3 sec)	45		ISO 868
<b>Thermal</b>	<b>Nominal Value</b>	<b>Unit</b>	
Brittleness Temperature	-45.0	°C	
Service Temperature			
Dynamic	110	°C	
Static	135	°C	

### Processing Information

<b>Injection</b>	<b>Nominal Value</b>	<b>Unit</b>
Hopper Temperature	170 to 180	°C
Middle Temperature	180 to 190	°C
Front Temperature	190 to 200	°C
Nozzle Temperature	200 to 210	°C
Processing (Melt) Temp	210 to 220	°C
Mold Temperature	10 to 50	°C
<b>Injection Notes</b>		
Max Allowable Melt Temperature: 250°C		
<b>Extrusion</b>	<b>Nominal Value</b>	<b>Unit</b>
Cylinder Zone 1 Temp.	170 to 190	°C
Cylinder Zone 3 Temp.	180 to 195	°C
Cylinder Zone 5 Temp.	195 to 205	°C
Adapter Temperature	200 to 210	°C
Die Temperature	200 to 220	°C

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.