



## EZPRENE VU-320-55A

### EZPRENE-V

<b>Product Description :</b>	This polyolefin based non-hygroscopic thermoplastic elastomer (TPE-V) compound is a dynamically vulcanized EPDM/PP blend with improved flow behaviour. EZPRENE® series are completely recyclable and can be processed with conventional thermoplastics machine
<b>Additive Packages :</b>	T / Heat and UV stabilizer /
<b>Key Features :</b>	Non-hygroscopic, no pre-drying Excellent ozone, UV and weathering resistance Rubberlike elasticity in a wide temperature range and low compression set Easy processing, faster cycle time over conventional TPVs Easy colorability with proper MB (PE, PP, e
<b>Process Method :</b>	Extrusion, coextrusion, blow molding, sheet extrusion, injection/multi injection molding
<b>Uses :</b>	Automotive, construction, home appliances, wire& cable, industrial applications

	Value	Unit	Standard
<b>Physical</b>			
Hardness	55	SHORE A	ISO 868 (3 second )
Density	0,98	gr / cm3	ISO 1183 1-A
Brittleness Point	-45	°C	*
<b>Mechanical</b>			
100% Modulus	1,6	Mpa	ISO 37, DIN 53504
300% Modulus	3,1	Mpa	ISO 37, DIN 53504
Tensile Strength At Break	6,6	Mpa	ISO 37, DIN 53504
Elongation at Break	540	%	ISO 37, DIN 53504
Tear Strength (Perpendicular to flow)	28	kN/m	ISO 34-1
<b>Aging</b>			
Compression Set (72h/23°C)	23	%	ASTM D 395-89-B
Compression Set (22h/70°C)	28	%	ASTM D 395-89-B
<b>Thermal</b>			
Max. Dynamic Service Temperature	110	°C	*
Max. Static Service Temperature	135	°C	*



Ravago Petrokimya



**EZPRENE VU-320-55A**

**EZPRENE-V**

**Environmental Resistance**

Ozone	Excellent
Water	Excellent
Alcohol	Excellent
Olive Oil	Fair
Sulphuric Acid	Good
Detergent	Good

**Drying Condition**

Drying Time(hr)	Not required
Drying Temperature(°C)	Not required

**Molding Condition (°C)**

1st Zone (hopper)(°C)	170-180
2nd Zone(°C)	180-190
3rd Zone(°C)	190-200
Nozzle(°C)	200-210
Melt Temperature(°C)	210-220
Mold Temperature(°C)	10-50
Max Allowable Melt Temperature(°C)	250 C

**Extrusion Condition (°C)**

Feed Zone Temperature (°C)	170 - 190
Compression Zone Temperature (°C)	180 - 195
Melting Zone Temperature (°C)	195 - 205
Extruder Head Temperature (°C)	200 - 210
Die Temperature (°C)	200 - 220

