

# CELCON® F10-03H

## CELCON®

- A stiffness-improved (high-viscosity) grade for general injection molding.
- Features greater stiffness compared to general POM copolymer.

### Product information

Resin Identification	POM	ISO 1043
Part Marking Code	>POM<	ISO 11469

### Rheological properties

Melt mass-flow rate	3 g/10min	ISO 1133
Melt mass-flow rate, Temperature	190 °C	
Melt mass-flow rate, Load	2.16 kg	
Moulding shrinkage, parallel	2.2 %	ISO 294-4, 2577

### Typical mechanical properties

Tensile modulus	2800 MPa	ISO 527-1/-2
Tensile stress at yield, 50mm/min	68 MPa	ISO 527-1/-2
Tensile strain at yield, 50mm/min	12 %	ISO 527-1/-2
Nominal strain at break	40 %	ISO 527-1/-2
Flexural modulus	2650 MPa	ISO 178
Flexural strength	90 MPa	ISO 178
Charpy notched impact strength, 23°C	7 kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30°C	6.5 kJ/m <sup>2</sup>	ISO 179/1eA
Poisson's ratio	0.39	

### Thermal properties

Melting temperature, 10°C/min	170 °C	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	100 °C	ISO 75-1/-2
Coefficient of linear thermal expansion (CLTE), parallel	120 E-6/K	ISO 11359-1/-2

### Electrical properties

Volume resistivity	1E12 Ohm.m	IEC 62631-3-1
Surface resistivity	1E16 Ohm	IEC 62631-3-2
Electric strength	19 kV/mm	IEC 60243-1

### Physical/Other properties

Humidity absorption, 2mm	0.2 %	Sim. to ISO 62
Density	1410 kg/m <sup>3</sup>	ISO 1183

### Injection

Drying Recommended	no
Drying Temperature	100 °C
Drying Time, Dehumidified Dryer	3 - 4 h
Processing Moisture Content	≤0.2 %
Melt Temperature Optimum	195 °C
Min. melt temperature	180 °C
Max. melt temperature	210 °C

# CELCON® F10-03H

## CELCON®

Screw tangential speed	≤0.3 m/s
Mold Temperature Optimum	70 °C
Min. mould temperature	60 °C
Max. mould temperature	80 °C
Hold pressure range	60 - 120 MPa

## Characteristics

Processing	Injection Moulding, Extrusion, Sheet Extrusion, Other Extrusion
Delivery form	Pellets

## Automotive

OEM	STANDARD	ADDITIONAL INFORMATION
General Motors	GMW22P-POM-C1	
Hyundai	MS237-05 Type E-1	Ulsan, Korea
Hyundai	MS237-14 Type A	Ulsan, Korea
Hyundai	MS941-03 Type M-1	Ulsan, Korea
Mercedes-Benz	DBL5405	Ulsan, Korea
Renault	Ulsan, Korea, No Spec, Special Part Approval, See Your CE Account Manager.	