

CELCON® F10-52H

CELCON®

- A UV-stabilized high-viscosity grade for general injection molding.
- Developed for applications in automotive interiors and exposed part

Product information

Resin Identification	POM	ISO 1043
Part Marking Code	>POM<	ISO 11469

Rheological properties

Melt mass-flow rate	4 g/10min	ISO 1133
Melt mass-flow rate, Temperature	190 °C	
Melt mass-flow rate, Load	2.16 kg	

Typical mechanical properties

Tensile stress at yield, 50mm/min	63 MPa	ISO 527-1/-2
Tensile strain at yield, 50mm/min	10 %	ISO 527-1/-2
Nominal strain at break	35 %	ISO 527-1/-2
Flexural modulus	2500 MPa	ISO 178
Flexural strength	83 MPa	ISO 178
Charpy notched impact strength, 23°C	8 kJ/m ²	ISO 179/1eA

Thermal properties

Melting temperature, 10°C/min	165 °C	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	85 °C	ISO 75-1/-2
Coefficient of linear thermal expansion (CLTE), parallel	120 E-6/K	ISO 11359-1/-2

Electrical properties

Volume resistivity	1E12 Ohm.m	IEC 62631-3-1
Surface resistivity	1E16 Ohm	IEC 62631-3-2

Physical/Other properties

Humidity absorption, 2mm	0.2 %	Sim. to ISO 62
Density	1400 kg/m ³	ISO 1183

Injection

Drying Recommended	no
Drying Temperature	100 °C
Drying Time, Dehumidified Dryer	3 - 4 h
Processing Moisture Content	≤0.2 %
Melt Temperature Optimum	195 °C
Min. melt temperature	180 °C
Max. melt temperature	210 °C
Screw tangential speed	≤0.3 m/s
Mold Temperature Optimum	70 °C
Min. mould temperature	60 °C
Max. mould temperature	80 °C
Hold pressure range	60 - 120 MPa

CELCON® F10-52H

CELCON®

Characteristics

Processing	Injection Moulding, Extrusion
Delivery form	Pellets
Special characteristics	U.V. stabilised or stable to weather

Automotive

OEM	STANDARD	ADDITIONAL INFORMATION
Hyundai	MS237-14 Type A	Ulsan, Korea