

CELCON® F20-03HC LOF2

CELCON®

CELCON® F20-03HC LOF2 is a medium-viscosity grade for general injection molding. Suitable for injection molding application with heat resistance-improved feature.

Product information

Resin Identification	POM	ISO 1043
Part Marking Code	>POM<	ISO 11469

Rheological properties

Melt mass-flow rate	9 g/10min	ISO 1133
Melt mass-flow rate, Temperature	190 °C	
Melt mass-flow rate, Load	2.16 kg	
Moulding shrinkage, parallel	2.0 %	ISO 294-4, 2577

Typical mechanical properties

Tensile stress at yield, 50mm/min	68 MPa	ISO 527-1/-2
Tensile strain at yield, 50mm/min	8 %	ISO 527-1/-2
Nominal strain at break	35 %	ISO 527-1/-2
Flexural modulus	2650 MPa	ISO 178
Flexural strength	90 MPa	ISO 178
Charpy notched impact strength, 23°C	6.5 kJ/m ²	ISO 179/1eA

Thermal properties

Melting temperature, 10°C/min	170 °C	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	100 °C	ISO 75-1/-2

Flammability

Burning Behav. at thickness h	HB class	IEC 60695-11-10
Thickness tested	3 mm	IEC 60695-11-10

Electrical properties

Volume resistivity	1E12 Ohm.m	IEC 62631-3-1
Surface resistivity	1E16 Ohm	IEC 62631-3-2
Electric strength	19 kV/mm	IEC 60243-1

Physical/Other properties

Humidity absorption, 2mm	0.2 %	Sim. to ISO 62
Density	1410 kg/m ³	ISO 1183

Characteristics

Processing	Injection Moulding
Delivery form	Pellets

CELCON® F20-03HC LOF2

CELCON®

Automotive

OEM
Hyundai

STANDARD
MS237-12 Type A

ADDITIONAL INFORMATION
Ulsan, Korea