

CELCON® LU02

CELCON®

Celcon® acetal copolymer grade LU02 is UV stabilized material displaying a reduced gloss over standard UV acetal grades.

Product information

| | | |
|----------------------|-------|-----------|
| Resin Identification | POM | ISO 1043 |
| Part Marking Code | >POM< | ISO 11469 |

Rheological properties

| | | |
|------------------------------|---------------------------|-----------------|
| Melt volume-flow rate | 20 cm ³ /10min | ISO 1133 |
| Temperature | 190 °C | |
| Load | 2.16 kg | |
| Moulding shrinkage, parallel | 1.9 % | ISO 294-4, 2577 |
| Moulding shrinkage, normal | 1.6 % | ISO 294-4, 2577 |

Typical mechanical properties

| | | |
|---------------------------------------|-----------------------|--------------|
| Tensile modulus | 2530 MPa | ISO 527-1/-2 |
| Tensile stress at yield, 50mm/min | 56 MPa | ISO 527-1/-2 |
| Tensile strain at yield, 50mm/min | 9 % | ISO 527-1/-2 |
| Nominal strain at break | 11 % | ISO 527-1/-2 |
| Flexural modulus | 2500 MPa | ISO 178 |
| Flexural stress at 3.5% | 67 MPa | ISO 178 |
| Charpy notched impact strength, 23°C | 3.7 kJ/m ² | ISO 179/1eA |
| Charpy notched impact strength, -30°C | 3.7 kJ/m ² | ISO 179/1eA |
| Poisson's ratio | 0.38 ^[C] | |

[C]: Calculated

Thermal properties

| | | |
|---|--------|----------------|
| Melting temperature, 10°C/min | 167 °C | ISO 11357-1/-3 |
| Temperature of deflection under load, 1.8 MPa | 90 °C | ISO 75-1/-2 |

Physical/Other properties

| | | |
|---------|------------------------|----------|
| Density | 1390 kg/m ³ | ISO 1183 |
|---------|------------------------|----------|

Injection

| | |
|---------------------------------|--------------|
| Drying Recommended | no |
| Drying Temperature | 100 °C |
| Drying Time, Dehumidified Dryer | 3 - 4 h |
| Processing Moisture Content | ≤0.2 % |
| Melt Temperature Optimum | 190 °C |
| Min. melt temperature | 180 °C |
| Max. melt temperature | 195 °C |
| Screw tangential speed | ≤0.3 m/s |
| Mold Temperature Optimum | 90 °C |
| Min. mould temperature | 80 °C |
| Max. mould temperature | 105 °C |
| Hold pressure range | 60 - 120 MPa |
| Back pressure | 4 MPa |

CELCON® LU02

CELCON®

Characteristics

| | |
|-------------------------|---|
| Processing | Injection Moulding |
| Delivery form | Pellets |
| Special characteristics | U.V. stabilised or stable to weather, Reduced gloss |

Additional information

Injection molding

Preprocessing

Drying is recommended for low gloss grades of Celcon® and Hostaform® acetal copolymers. Excessive moisture can lead to splay (silver streaking) in molded parts. For better uniformity in molding especially when using regrind or material that has been stored in containers open to the atmosphere, recommended drying conditions are 80 C (180 F) for 3hours. Desiccant hopper dryers are not required. Maximum water content = 0.35%

Processing

Standard reciprocating screw injection molding machines with a high compression screw (minimum 3:1 and preferably 4:1) and low back pressure (0.35 Mpa/50 PSI) are favored. Using a low compression screw (I.E. general purpose 2:1 compression ratio) can result in unmelted particles and poor melt homogeneity. Using a high back pressure to make up for a low compression ratio may lead to excessive shear heating and deterioration of the material.

Use a slow injection speed until material passes through the gate.

Melt Temperature: Preferred range 180-195 C (~356~383 F). Melt temperature should never exceed 230 C (450 F).

Mold Surface Temperature: Preferred range 80-105 C especially with wall thickness less than 1.5 mm (0.060 in.). May require mold temperature as high as 120 C (250 F) to reproduce mold surface or to assure minimal molded in stress. In general, mold surface temperatures lower than 82 C (180 F) may produce a hazy surface or a surface with flow lines, pits and other included defects.

Postprocessing

Postprocessing conditioning and moisturizing are not required. It may be necessary to fixture large or complicated parts with varying wall thickness to prevent warpage while cooling to ambient temperature.

Pre-Drying

Predrying is required before processing to ensure a low gloss finish.

Processing Notes

CELCON® LU02

CELCON®

Automotive

OEM

Honda

Nissan

ADDITIONAL INFORMATION

Color approved

Color approved