

HOSTAFORM® LM270Z XAP®2

HOSTAFORM®

Hostaform® acetal copolymer grade LX270Z XAP®2 is a UV stabilized material available in a range of molded in metallic colors generally for automotive interior applications and is a higher flow grade than LX90Z. In addition, Hostaform® LX270Z XAP®2 has lower volatile emissions as required for some automotive interiors. Flow properties of this grade is based upon the uncolored acetal copolymer and flow testing does not reflect how it actually flows. Besides material, optimal finish for specialty metallic parts is dependent on proper drying, gate design, knit line locations, and special processing. Please contact Celanese Technical Service for assistance with your application.

Product information

Resin Identification	POM	ISO 1043
Part Marking Code	>POM<	ISO 11469

Rheological properties

Melt volume-flow rate	24 cm ³ /10min	ISO 1133
Temperature	190 °C	
Load	2.16 kg	

Typical mechanical properties

Tensile modulus	2600 MPa	ISO 527-1/-2
Tensile stress at yield, 50mm/min	62 MPa	ISO 527-1/-2
Tensile strain at yield, 50mm/min	7.5 %	ISO 527-1/-2
Charpy notched impact strength, 23 °C	5.5 kJ/m ²	ISO 179/1eA
Poisson's ratio	0.38 ^[C]	

[C]: Calculated

Thermal properties

Melting temperature, 10 °C/min	164 °C	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	100 °C	ISO 75-1/-2
Coefficient of linear thermal expansion (CLTE), parallel	110 E-6/K	ISO 11359-1/-2
Coefficient of linear thermal expansion (CLTE), normal	110 E-6/K	ISO 11359-1/-2

Physical/Other properties

Humidity absorption, 2mm	0.2 %	Sim. to ISO 62
Water absorption, 2mm	0.65 %	Sim. to ISO 62
Density	1410 kg/m ³	ISO 1183

Injection

Drying Recommended	no
Drying Temperature	100 °C
Drying Time, Dehumidified Dryer	3 - 4 h
Processing Moisture Content	≤0.2 %
Melt Temperature Optimum	190 °C
Min. melt temperature	180 °C
Max. melt temperature	200 °C
Screw tangential speed	≤0.3 m/s
Mold Temperature Optimum	100 °C
Min. mould temperature	80 °C

HOSTAFORM® LM270Z XAP®2

HOSTAFORM®

Max. mould temperature	120 °C
Hold pressure range	60 - 120 MPa
Back pressure	4 MPa

Characteristics

Processing	Injection Moulding
Delivery form	Granules
Special characteristics	Light stabilised or stable to light, U.V. stabilised or stable to weather, Laser Markable, High Flow, Low emissions

Additional information

Injection molding

Preprocessing

To achieve low emission values pre drying using a recirculating air dryer (100 to 120 °C / max. 40 mm layer / 3 to 6 hours) is recommended.

Max. Water content 0,1 %

Processing

Standard injection moulding machines with three phase (15 to 25 D) plasticating screws will fit.

Melt temperature 180-190 °C
Mould temperature 60-120 °C

Postprocessing

Conditioning e.g. moisturizing is not necessary.

Processing Notes

Pre-Drying

recommended

Automotive

OEM
VW Group

STANDARD
TL 524 76

ADDITIONAL INFORMATION
10/9222 Black