

# HOSTAFORM® S 9362 XAP®2

## HOSTAFORM®

Hostaform® acetal copolymer grade S 9362 XAP®2 is an impact modified grade for applications requiring improved impact. Hostaform® S 9362 XAP®2 provides good impact strength while improving modulus and weld line strength over standard impact modified grades, and also exhibits exceptional low emission performance meeting or exceeding the requirements of many automotive markets. Chemical abbreviation according to ISO 1043-1: POM-HI

### Product information

Resin Identification	POM	ISO 1043
Part Marking Code	>POM<	ISO 11469

### Rheological properties

Melt volume-flow rate	6.5 cm <sup>3</sup> /10min	ISO 1133
Temperature	190 °C	
Load	2.16 kg	
Moulding shrinkage, parallel	1.9 %	ISO 294-4, 2577
Moulding shrinkage, normal	1.8 %	ISO 294-4, 2577

### Typical mechanical properties

Tensile modulus	2300 MPa	ISO 527-1/-2
Tensile stress at yield, 50mm/min	55 MPa	ISO 527-1/-2
Tensile strain at yield, 50mm/min	10 %	ISO 527-1/-2
Flexural modulus	2200 MPa	ISO 178
Charpy impact strength, 23°C	N kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength, -30°C	190 kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, 23°C	10 kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30°C	6 kJ/m <sup>2</sup>	ISO 179/1eA
Izod notched impact strength, 23°C	10 kJ/m <sup>2</sup>	ISO 180/1A
Izod notched impact strength, -40°C	6.0 kJ/m <sup>2</sup>	ISO 180/1A
Hardness, Rockwell, M-scale	75	ISO 2039-2
Poisson's ratio	0.39 <sup>[C]</sup>	

[C]: Calculated

### Thermal properties

Melting temperature, 10°C/min	165 °C	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	87 °C	ISO 75-1/-2
Temperature of deflection under load, 0.45 MPa	151 °C	ISO 75-1/-2
Coefficient of linear thermal expansion (CLTE), parallel	110 E-6/K	ISO 11359-1/-2
Coefficient of linear thermal expansion (CLTE), normal	110 E-6/K	ISO 11359-1/-2

### Physical/Other properties

Humidity absorption, 2mm	0.25 %	Sim. to ISO 62
Water absorption, 2mm	0.8 %	Sim. to ISO 62
Density	1390 kg/m <sup>3</sup>	ISO 1183

# HOSTAFORM® S 9362 XAP® 2

## HOSTAFORM®

### Injection

Drying Recommended	no
Drying Temperature	100 °C
Drying Time, Dehumidified Dryer	3 - 4 h
Processing Moisture Content	≤0.2 %
Melt Temperature Optimum	190 °C
Min. melt temperature	180 °C
Max. melt temperature	200 °C
Screw tangential speed	≤0.3 m/s
Mold Temperature Optimum	100 °C
Min. mould temperature	80 °C
Max. mould temperature	120 °C
Hold pressure range	60 - 120 MPa
Back pressure	2 MPa

### Characteristics

Processing	Injection Moulding, Extrusion
Delivery form	Pellets
Additives	Release agent
Special characteristics	High impact or impact modified, Low emissions

### Additional information

Processing Notes

### Pre-Drying

Drying is suggested to help achieve low emission performance and to counter if material has contacted moisture through improper storage and handling.

### Automotive

OEM	STANDARD	ADDITIONAL INFORMATION
Mercedes-Benz	DBL5404	BQF
Renault	No Spec, Special Part Approval, See Your CE Account Manager.	