

HOSTAFORM® S 9364

HOSTAFORM®

Hostaform® acetal copolymer grade S 9364 is highly impact modified grade for demanding applications. Hostaform® S 9364 provides a significant improvement in impact strength and flexibility over standard impact modified grades. Chemical abbreviation according to ISO 1043-1: POM-HI.

Product information

Resin Identification	POM-I	ISO 1043
Part Marking Code	>POM-I<	ISO 11469

Rheological properties

Melt volume-flow rate	4 cm ³ /10min	ISO 1133
Temperature	190 °C	
Load	2.16 kg	
Moulding shrinkage, parallel	1.6 %	ISO 294-4, 2577
Moulding shrinkage, normal	1.5 %	ISO 294-4, 2577

Typical mechanical properties

Tensile modulus	1650 MPa	ISO 527-1/-2
Tensile stress at yield, 50mm/min	43 MPa	ISO 527-1/-2
Tensile strain at yield, 50mm/min	16 %	ISO 527-1/-2
Flexural modulus	1550 MPa	ISO 178
Flexural stress at 3.5%	42 MPa	ISO 178
Charpy impact strength, 23°C	N kJ/m ²	ISO 179/1eU
Charpy impact strength, -30°C	N kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 23°C	21 kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	11 kJ/m ²	ISO 179/1eA
Izod notched impact strength, 23°C	20 kJ/m ²	ISO 180/1A
Izod notched impact strength, -30°C	12.0 kJ/m ²	ISO 180/1A
Izod notched impact strength, -40°C	10.0 kJ/m ²	ISO 180/1A
Izod impact strength, 23°C	N kJ/m ²	ISO 180/1U
Izod impact strength, -30°C	N kJ/m ²	ISO 180/1U
Hardness, Rockwell, M-scale	48	ISO 2039-2
Poisson's ratio	0.43	
Shore D hardness, 15s	76	ISO 48-4 / ISO 868

Thermal properties

Melting temperature, 10°C/min	165 °C	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	75 °C	ISO 75-1/-2
Temperature of deflection under load, 0.45 MPa	140 °C	ISO 75-1/-2
Coefficient of linear thermal expansion (CLTE), parallel	120 E-6/K	ISO 11359-1/-2
Coefficient of linear thermal expansion (CLTE), normal	110 E-6/K	ISO 11359-1/-2

Physical/Other properties

Humidity absorption, 2mm	0.25 %	Sim. to ISO 62
Water absorption, 2mm	0.8 %	Sim. to ISO 62
Density	1360 kg/m ³	ISO 1183

HOSTAFORM® S 9364

HOSTAFORM®

Injection

Drying Recommended	no
Drying Temperature	100 °C
Drying Time, Dehumidified Dryer	3 - 4 h
Processing Moisture Content	≤0.2 %
Melt Temperature Optimum	195 °C
Min. melt temperature	180 °C
Max. melt temperature	210 °C
Screw tangential speed	≤0.3 m/s
Mold Temperature Optimum	65 °C
Min. mould temperature	60 °C
Max. mould temperature	70 °C
Hold pressure range	60 - 120 MPa
Back pressure	2 MPa
Ejection temperature	127 °C

Characteristics

Processing	Injection Moulding, Extrusion
Delivery form	Pellets
Additives	Release agent
Special characteristics	High impact or impact modified

Additional information

Processing Notes

Pre-Drying

Drying is not normally required. If material has come in contact with moisture through improper storage or handling or through regrind use, drying to prevent splay and odor problems.


Automotive

OEM	STANDARD	ADDITIONAL INFORMATION
Changan	MTS-F01-02-001-A3	2019
Chery	Q/SQR S1-19-2023	
Ford	WSK-M4D618-A2	
Li Auto	Q/LiA5310020	2021 (V2)
Renault	No spec listed	
Stellantis	MS.502xx / POM-C.1550F.10C.TG	CPN3379 CANOD, CPN5237 BLK
Stellantis - Chrysler	MS.50095 / CPN-3379	Canod
Stellantis - Chrysler	MS.50095 / CPN-5237	Black

HOSTAFORM® S 9364

HOSTAFORM®


Stress-strain



HOSTAFORM® S 9364

HOSTAFORM®


Secant modulus-strain



HOSTAFORM® S 9364

HOSTAFORM®

Stress-strain, 50mm/min



HOSTAFORM® S 9364

HOSTAFORM®

Secant modulus-strain, 50mm/min

