

HOSTAFORM® XGC25 EF XAP®2

High strength glass coupled, easy flow

Hostaform® XGC25 EF XAP®2 is an easy flowing injection molding grade with approximately 25% glass fibers and reduced emission.

Emissions according to VDA 275 < 5ppm [mg/kg]

Rheological properties

Melt volume-flow rate	5 cm ³ /10min	ISO 1133
Temperature	190 °C	
Load	2.16 kg	
Moulding shrinkage range, parallel	0.5 %	ISO 294-4, 2577
Moulding shrinkage range, normal	1.1 %	ISO 294-4, 2577

Typical mechanical properties

Tensile Modulus	9000 MPa	ISO 527-1/-2
Stress at break, 5mm/min	155 MPa	ISO 527-1/-2
Strain at break, 5mm/min	3 %	ISO 527-1/-2
Charpy impact strength, 23°C	65 kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 23°C	11 kJ/m ²	ISO 179/1eA

Thermal properties

Melting temperature, 10°C/min	166 °C	ISO 11357-1/-3
Temp. of deflection under load, 1.8 MPa	160 °C	ISO 75-1/-2

Other properties


Density	1580 kg/m ³	ISO 1183
---------	------------------------	----------

Injection

Drying Temperature	100 - 120 °C	
Drying Time, Dehumidified Dryer	3 - 4 h	
Processing Moisture Content	0.15 %	
Melt Temperature Optimum	200 °C	Internal
Screw tangential speed	0.2 - 0.21 m/s	
Max. mould temperature	80 - 120 °C	
Back pressure	2 MPa	
Injection speed	slow	

HOSTAFORM® XGC25 EF XAP®2

Stress-strain



HOSTAFORM® XGC25 EF XAP®2

Secant modulus-strain

