

# KEPITAL® F10-02

A high-viscosity grade for extrusion of round bars, sheets and tubes

- A high-viscosity grade for extrusion of round bars, sheets and tubes

- Suitable for extrusion molding of thick-walled, void-free, and sink mark-reduced parts

## Rheological properties

Moulding shrinkage range, parallel	2.0 %	ISO 294-4, 2577
------------------------------------	-------	-----------------

## Typical mechanical properties

Tensile Modulus	2600 MPa	ISO 527-1/-2
Yield stress, 50mm/min	63 MPa	ISO 527-1/-2
Yield strain, 50mm/min	10 %	ISO 527-1/-2
Nominal strain at break	32 %	ISO 527-1/-2
Flexural Modulus	2400 MPa	ISO 178
Flexural Strength	84 MPa	ISO 178
Charpy notched impact strength, 23°C	8 kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30°C	6.5 kJ/m <sup>2</sup>	ISO 179/1eA

## Thermal properties

Melting temperature, 10°C/min	165 °C	ISO 11357-1/-3
Temp. of deflection under load, 1.8 MPa	96 °C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	120 E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	120 E-6/K	ISO 11359-1/-2

## Flammability

Burning Behav. at thickness h	HB class	UL 94
-------------------------------	----------	-------

## Electrical properties

Volume resistivity	>1E14 Ohm.m	IEC 62631-3-1
Surface resistivity	>1E16 Ohm	IEC 62631-3-2
Electric strength	19 kV/mm	IEC 60243-1

## Other properties

Water absorption, 2mm	0.2 %	Sim. to ISO 62
Density	1410 kg/m <sup>3</sup>	ISO 1183

## Other Approvals

Other Approvals

OEM	Specification	Additional Information
GM	GMP.POM.012	Natural & Black