

# KEPITAL® F20-52

a UV-stabilized medium-viscosity grade for general injection molding

KEPITAL® F20-52 is a UV-stabilized medium-viscosity grade for general injection molding. Developed for applications in automotive interiors and exposed parts.

## Rheological properties

Moulding shrinkage range, parallel	2.0 %	ISO 294-4, 2577
------------------------------------	-------	-----------------

## Typical mechanical properties

Tensile Modulus	2600 MPa	ISO 527-1/-2
Yield stress, 50mm/min	63 MPa	ISO 527-1/-2
Yield strain, 50mm/min	10 %	ISO 527-1/-2
Nominal strain at break	34 %	ISO 527-1/-2
Flexural Modulus	2350 MPa	ISO 178
Flexural Strength	83 MPa	ISO 178
Charpy notched impact strength, 23°C	6 kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30°C	5.5 kJ/m <sup>2</sup>	ISO 179/1eA

## Thermal properties

Melting temperature, 10°C/min	165 °C	ISO 11357-1/-3
Temp. of deflection under load, 1.8 MPa	92 °C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	130 E-6/K	ISO 11359-1/-2

## Electrical properties

Electric strength	19 kV/mm	IEC 60243-1
-------------------	----------	-------------

## Other properties

Humidity absorption, 2mm	0.2 %	Sim. to ISO 62
Density	1410 kg/m <sup>3</sup>	ISO 1183

## Other Approvals

Other Approvals

OEM	Specification	Additional Information
GM	EDS-M-5205-11	
GM	GMP.POM.008	Natural