

# KEPITAL® F25-03 LOF

unfilled, medium-low viscosity grade; low emission  
 - A Standard unfilled (medium-low viscosity) grade for general injection molding  
 - A low-emission grade featuring improved heat stability

## Rheological properties

Moulding shrinkage range, parallel	2.0 %	ISO 294-4, 2577
------------------------------------	-------	-----------------

## Typical mechanical properties

Tensile Modulus	2750 MPa	ISO 527-1/-2
Yield stress, 50mm/min	65 MPa	ISO 527-1/-2
Yield strain, 50mm/min	9 %	ISO 527-1/-2
Nominal strain at break	33 %	ISO 527-1/-2
Flexural Modulus	2650 MPa	ISO 178
Charpy notched impact strength, 23°C	6 kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30°C	5.5 kJ/m <sup>2</sup>	ISO 179/1eA
Poisson's ratio	0.366	

## Thermal properties

Melting temperature, 10°C/min	165 °C	ISO 11357-1/-3
Temp. of deflection under load, 1.8 MPa	100 °C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	120 E-6/K	ISO 11359-1/-2

## Electrical properties

Surface resistivity	>1E15 Ohm	IEC 62631-3-2
Electric strength	19 kV/mm	IEC 60243-1

## Other properties

Humidity absorption, 2mm	0.2 %	Sim. to ISO 62
Density	1410 kg/m <sup>3</sup>	ISO 1183