

# KEPITAL® F40-03 Colored

An extremely low-viscosity grade for general injection molding (colored)

KEPITAL® F40-03 Colored is a standard unfilled(extremely low-viscosity) grade for general injection molding (colored).

Suitable for multi-cavity molds and thin-walled precision parts

## Rheological properties

Moulding shrinkage range, parallel	2.0 %	ISO 294-4, 2577
------------------------------------	-------	-----------------

## Typical mechanical properties

Yield stress, 50mm/min	65 MPa	ISO 527-1/-2
Yield strain, 50mm/min	7 %	ISO 527-1/-2
Nominal strain at break	20 %	ISO 527-1/-2
Flexural Modulus	2750 MPa	ISO 178
Flexural Strength	93 MPa	ISO 178
Charpy notched impact strength, 23°C	3.5 kJ/m <sup>2</sup>	ISO 179/1eA

## Thermal properties

Melting temperature, 10°C/min	165 °C	ISO 11357-1/-3
Temp. of deflection under load, 1.8 MPa	101 °C	ISO 75-1/-2

## Flammability

Burning Behav. at thickness h	HB class	UL 94
-------------------------------	----------	-------

## Other properties

Humidity absorption, 2mm	0.2 %	Sim. to ISO 62
Density	1410 kg/m <sup>3</sup>	ISO 1183