

KEPITAL® FU2020W

toughened, medium-high viscosity grade

KEPITAL® FU2020W is a toughened, medium-high viscosity grade for general injection molding. Suitable for applications requiring much higher impact resistance and toughness than KEPITAL® TE-24.

Rheological properties

Moulding shrinkage range, parallel	1.6 %	ISO 294-4, 2577
------------------------------------	-------	-----------------

Typical mechanical properties

Yield stress, 50mm/min	39 MPa	ISO 527-1/-2
Yield strain, 50mm/min	14 %	ISO 527-1/-2
Nominal strain at break	>50 %	ISO 527-1/-2
Flexural Modulus	1250 MPa	ISO 178
Flexural Strength	46 MPa	ISO 178
Charpy notched impact strength, 23°C	21 kJ/m ²	ISO 179/1eA

Thermal properties

Melting temperature, 10°C/min	165 °C	ISO 11357-1/-3
Temp. of deflection under load, 1.8 MPa	65 °C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	130 E-6/K	ISO 11359-1/-2

Flammability

Burning Behav. at thickness h	HB class	UL 94
-------------------------------	----------	-------

Electrical properties

Electric strength	21 kV/mm	IEC 60243-1
-------------------	----------	-------------

Other properties

Density	1340 kg/m ³	ISO 1183
---------	------------------------	----------