

# KEPITAL® TS-25H

A silicone-modified wear resistance grade for general injection molding

A silicone-modified wear resistance grade for general injection molding. Designed for applications requiring a high PV limit, low wear and low friction.

## Rheological properties

Moulding shrinkage range, parallel	2.0 %	ISO 294-4, 2577
------------------------------------	-------	-----------------

## Typical mechanical properties

Yield stress, 50mm/min	59 MPa	ISO 527-1/-2
Yield strain, 50mm/min	9 %	ISO 527-1/-2
Nominal strain at break	23 %	ISO 527-1/-2
Flexural Modulus	2550 MPa	ISO 178
Flexural Strength	83 MPa	ISO 178
Charpy notched impact strength, 23°C	5.5 kJ/m <sup>2</sup>	ISO 179/1eA

## Thermal properties

Melting temperature, 10°C/min	168 °C	ISO 11357-1/-3
Temp. of deflection under load, 1.8 MPa	98 °C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	130 E-6/K	ISO 11359-1/-2

## Electrical properties

Volume resistivity	>1E12 Ohm.m	IEC 62631-3-1
Surface resistivity	>1E16 Ohm	IEC 62631-3-2

## Other properties

Humidity absorption, 2mm	0.2 %	Sim. to ISO 62
Density	1390 kg/m <sup>3</sup>	ISO 1183

---