

KEPITAL® TS-25HN

a lubricated and wear resistant grade.

KEPITAL® TS-25HN is a lubricated and wear resistant grade.

Rheological properties

Moulding shrinkage range, parallel	2.0 %	ISO 294-4, 2577
------------------------------------	-------	-----------------

Typical mechanical properties

Yield stress, 50mm/min	58 MPa	ISO 527-1/-2
Nominal strain at break	25 %	ISO 527-1/-2
Flexural Modulus	2500 MPa	ISO 178
Flexural Strength	80 MPa	ISO 178
Charpy notched impact strength, 23°C	8 kJ/m ²	ISO 179/1eA

Thermal properties

Melting temperature, 10°C/min	168 °C	ISO 11357-1/-3
Temp. of deflection under load, 1.8 MPa	98 °C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	130 E-6/K	ISO 11359-1/-2

Electrical properties

Volume resistivity	>1E16 Ohm.m	IEC 62631-3-1
Surface resistivity	>1E16 Ohm	IEC 62631-3-2

Other properties

Humidity absorption, 2mm	0.2 %	Sim. to ISO 62
Density	1390 kg/m ³	ISO 1183
