

KEPITAL® TX-21 LOF

POM, polymer-modified wear-resistance, medium-viscosity grade for general injection molding, low emission
 - A polymer-modified wear-resistance grade (medium-viscosity) for general injection molding.
 - Suitable for applications requiring reduced wear noise and a strong friction and wear resistance without sacrificing mechanical properties and a low-emission grade featuring improved heat stability.

Product information

| | | |
|-------------------|---------|-----------|
| Part Marking Code | > POM < | ISO 11469 |
|-------------------|---------|-----------|

Rheological properties

| | | |
|------------------------------------|-------|-----------------|
| Moulding shrinkage range, parallel | 2.0 % | ISO 294-4, 2577 |
|------------------------------------|-------|-----------------|

Typical mechanical properties

| | | |
|---------------------------------------|-----------------------|--------------|
| Tensile Modulus | 2500 MPa | ISO 527-1/-2 |
| Yield stress, 50mm/min | 57 MPa | ISO 527-1/-2 |
| Yield strain, 50mm/min | 10 % | ISO 527-1/-2 |
| Nominal strain at break | 33 % | ISO 527-1/-2 |
| Flexural Modulus | 2350 MPa | ISO 178 |
| Flexural Strength | 79 MPa | ISO 178 |
| Charpy notched impact strength, 23°C | 7.5 kJ/m ² | ISO 179/1eA |
| Charpy notched impact strength, -30°C | 5 kJ/m ² | ISO 179/1eA |

Thermal properties

| | | |
|---|-----------|----------------|
| Melting temperature, 10°C/min | 165 °C | ISO 11357-1/-3 |
| Temp. of deflection under load, 1.8 MPa | 90 °C | ISO 75-1/-2 |
| Coeff. of linear therm. expansion, parallel | 130 E-6/K | ISO 11359-1/-2 |

Electrical properties

| | | |
|---------------------|-------------|---------------|
| Volume resistivity | >1E12 Ohm.m | IEC 62631-3-1 |
| Surface resistivity | >1E16 Ohm | IEC 62631-3-2 |
| Electric strength | 19 kV/mm | IEC 60243-1 |

Other properties

| | | |
|--------------------------|------------------------|----------------|
| Humidity absorption, 2mm | 0.2 % | Sim. to ISO 62 |
| Density | 1390 kg/m ³ | ISO 1183 |