

CELSTRAN® PP-GF30-0501 P8/13

PP with 30% ash content - impact modified

Material code according to ISO 1043-1: PP High impact modified polypropylene reinforced with 30 weight percent long glass fibers. Black. The fibers are chemically coupled to the polypropylene matrix. The impact properties are enhanced. The pellets are cylindrical and normally as well as the embedded fibers 8 mm long. Parts molded of CELSTRAN have outstanding mechanical properties such as high strength and stiffness combined with high heat deflection. The notched impact strength is increased at elevated and low temperatures due to the fiber skeleton built in the parts. The long fiber reinforcement reduces creep significantly. The very isotropic shrinkage in the molded parts minimizes the warpage. Complex parts can be manufactured with high reproducibility by injection molding. Application field: Functional/structural parts for automotive

Typical mechanical properties

Tensile Modulus	6400 MPa	ISO 527-1/-2
Stress at break, 5mm/min	95 MPa	ISO 527-1/-2
Strain at break, 5mm/min	2.6 %	ISO 527-1/-2
Flexural Modulus	5500 MPa	ISO 178
Flexural Strength	140 MPa	ISO 178
Charpy impact strength, 23°C	70 kJ/m ²	ISO 179/1eU
Charpy impact strength, -30°C	80 kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 23°C	29 kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	28 kJ/m ²	ISO 179/1eA

Thermal properties

Temp. of deflection under load, 1.8 MPa	158 °C	ISO 75-1/-2
Temp. of deflection under load, 8 MPa	122 °C	ISO 75-1/-2

Other properties

Density	1120 kg/m ³	ISO 1183
---------	------------------------	----------

Injection

Drying Temperature	90 - 100 °C
Drying Time, Dehumidified Dryer	2 h
Processing Moisture Content	0.2 %
Screw tangential speed	0.1 m/s
Max. mould temperature	30 - 70 °C
Back pressure	3 MPa
Injection speed	slow

Processing Texts

Pre-drying It is normally not necessary to dry CELSTRAN PP. However, should there be surface moisture (condensate) on the molding compound as a result of incorrect storage, drying is required.

Longer pre-drying times/storage The product can then be stored in standard conditions until processed.