

OMNIPRO® CPP R GRC20 BK2000

OMNIPRO®

Product information

Resin Identification	PP-GF20	ISO 1043
Part Marking Code	>PP-GF20<	ISO 11469

Rheological properties

Melt mass-flow rate	12 g/10min	ISO 1133
Melt mass-flow rate, Temperature	230 °C	
Melt mass-flow rate, Load	2.16 kg	

Typical mechanical properties

Tensile modulus	4900 MPa	ISO 527-1/-2
Tensile stress at break, 5mm/min	60 MPa	ISO 527-1/-2
Tensile strain at break, 5mm/min	4 %	ISO 527-1/-2
Flexural modulus	5050 MPa	ISO 178
Charpy notched impact strength, 23°C	7 kJ/m ²	ISO 179/1eA
Poisson's ratio	0.35 ^[C]	
[C]: Calculated		

Physical/Other properties

Density	1040 kg/m ³	ISO 1183
---------	------------------------	----------