

OMNIPRO® CPP TF20 UV

OMNIPRO®

Copolymer PP. 20% Talc-filled. UV stabilized.

Product information

Resin Identification	PP-T20	ISO 1043
Part Marking Code	>PP-T20<	ISO 11469

Rheological properties

Melt mass-flow rate, Temperature	230 °C
Melt mass-flow rate, Load	2.16 kg

Typical mechanical properties

Izod notched impact strength, 23°C	4.3 kJ/m ²	ISO 180/1A
------------------------------------	-----------------------	------------

Flammability

FMVSS Class	B	ISO 3795 (FMVSS 302)
Burning rate, Thickness 1 mm	78.2 mm/min	ISO 3795 (FMVSS 302)

Physical/Other properties

Density	1040 kg/m ³	ISO 1183
---------	------------------------	----------