

OMNIPRO® HPP GRC20

OMNIPRO®

Homopolymer Polypropylene. 20% Glass Reinforced.

Product information

Resin Identification	PP-GF20	ISO 1043
Part Marking Code	>PP-GF20<	ISO 11469

Rheological properties

Melt mass-flow rate	6 g/10min	ISO 1133
Melt mass-flow rate, Temperature	230 °C	
Melt mass-flow rate, Load	2.16 kg	

Typical mechanical properties

Tensile modulus	5200 MPa	ISO 527-1/-2
Tensile stress at break, 5mm/min	74 MPa	ISO 527-1/-2
Tensile strain at break, 5mm/min	3.4 %	ISO 527-1/-2
Flexural modulus	5000 MPa	ISO 178
Flexural strength	120 MPa	ISO 178
Charpy impact strength, 23 °C	9.5 kJ/m ²	ISO 179/1eU
Poisson's ratio	0.35 ^[C]	

[C]: Calculated

Physical/Other properties

Density	1040 kg/m ³	ISO 1183
---------	------------------------	----------