

---

**POLIFOR® 15 T/20 H-R NERO X1 - PP**


---

**Description**


---

Polypropylene, homopolymer, 20% mineral filled, heat and copper contact stabilized

Physical properties	Value	Unit	Test Standard
Density	1070	kg/m <sup>3</sup>	ISO 1183
Melt flow rate, MFR	11.5	g/10min	ISO 1133
MFR temperature	230	°C	ISO 1133
MFR load	2.16	kg	ISO 1133

Mechanical properties	Value	Unit	Test Standard
Tensile stress at yield, 50mm/min	30	MPa	ISO 527-2/1A
Tensile strain at break, 50mm/min	20	%	ISO 527-2/1A
Flexural modulus, 23°C	2500	MPa	ISO 178
Charpy impact strength, 23°C	50	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, 23°C	2.3	kJ/m <sup>2</sup>	ISO 179/1eA
Izod impact notched, 23°C	3	kJ/m <sup>2</sup>	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
Vicat softening temperature, 50°C/h 50N	93	°C	ISO 306
Flammability @1.6mm nom. thickn.	HB	class	UL 94

**Typical injection moulding processing conditions**


---

Pre Drying	Value	Unit	Test Standard
Drying time	2 - 3	h	-
Drying temperature	80 - 100	°C	-
Temperature	Value	Unit	Test Standard
Zone1 temperature	190 - 210	°C	-
Zone2 temperature	210 - 230	°C	-
Zone3 temperature	220 - 240	°C	-
Melt temperature	230 - 250	°C	-
Mold temperature	30 - 60	°C	-

**Other text information**


---

**Longer pre-drying times/storage**


---

This product should be stored in a covered facility and kept away from moisture and heat.

**Characteristics**


---

Product Categories	Additives
Mineral reinforced	Metal deactivator

**Processing**


---

Injection molding