

# POLIFOR® 5000/V2

Polypropylene, homopolymer, UL94 V2, PBDE free

## Rheological properties

Melt mass-flow rate	14 g/10min	ISO 1133
Melt mass-flow rate, Temperature	230 °C	
Melt mass-flow rate, Load	2.16 kg	

## Typical mechanical properties

Yield stress, 50mm/min	32 MPa	ISO 527-1/-2
Flexural Modulus	1500 MPa	ISO 178
Charpy impact strength, 23°C	>80 kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, 23°C	2.4 kJ/m <sup>2</sup>	ISO 179/1eA
Izod impact strength, 23°C	2.5 kJ/m <sup>2</sup>	ISO 180/1U

## Flammability

Burning Behav. at 1.5mm nom. thickn.	V-2 class	UL 94
Burning Behav. at thickness h	V-2 class	UL 94
Thickness tested	0.75 mm	UL 94
UL recognition	yes	UL 94
Glow Wire Flammability Index, 3mm	960 °C	IEC 60695-2-12

## Other properties

Density	930 kg/m <sup>3</sup>	ISO 1183
---------	-----------------------	----------

## Injection

Drying Temperature	80 - 100 °C
Drying Time, Dehumidified Dryer	2 - 3 h
Max. mould temperature	30 - 60 °C

## Characteristics

Additives	Flame retardant
-----------	-----------------

## Processing Texts

Longer pre-drying times/storage	This product should be stored in a covered facility and kept away from moisture and heat.
---------------------------------	---