

## POLIFOR® 8 T/20 H-R NERO GWT 750 - PP

### Description

Polypropylene, homopolymer, 20% talc filled, heat and copper contact stabilized

Physical properties	Value	Unit	Test Standard
Density	1070	kg/m <sup>3</sup>	ISO 1183
Melt flow rate, MFR	8	g/10min	ISO 1133
MFR temperature	230	°C	ISO 1133
MFR load	2.16	kg	ISO 1133

Mechanical properties	Value	Unit	Test Standard
Tensile stress at yield, 50mm/min	34	MPa	ISO 527-2/1A
Flexural modulus, 23°C	3500	MPa	ISO 178
Flexural strength, 23°C	55	MPa	ISO 178
Charpy impact strength, 23°C	40	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, 23°C	2	kJ/m <sup>2</sup>	ISO 179/1eA
Izod impact notched, 23°C	2.5	kJ/m <sup>2</sup>	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
Vicat softening temperature, 50°C/h 50N	105	°C	ISO 306
Flammability @1.6mm nom. thickn.	HB	class	UL 94
Glow wire flammability index, 3.2 mm	750	°C	IEC 60695-2-12

### Typical injection moulding processing conditions

Pre Drying	Value	Unit	Test Standard
Drying time	2 - 3	h	-
Drying temperature	80 - 100	°C	-
Temperature	Value	Unit	Test Standard
Zone1 temperature	190 - 210	°C	-
Zone2 temperature	210 - 230	°C	-
Zone3 temperature	220 - 240	°C	-
Melt temperature	230 - 250	°C	-
Mold temperature	30 - 60	°C	-

### Other text information

#### Longer pre-drying times/storage

This product should be stored in a covered facility and kept away from moisture and heat.

### Characteristics

Product Categories	Additives
Mineral reinforced	Metal deactivator

### Processing

Injection molding