

# POLIFOR® C10 T/10 UV

## POLIFOR®

Polypropylene copolymer, 10% mineral filled, UV stabilised

### Product information

Resin Identification	PP-T10	ISO 1043
Part Marking Code	>PP-T10<	ISO 11469

### Rheological properties

Melt mass-flow rate	8 g/10min	ISO 1133
Melt mass-flow rate, Temperature	230 °C	
Melt mass-flow rate, Load	2.16 kg	

### Typical mechanical properties

Tensile stress at yield, 50mm/min	25 MPa	ISO 527-1/-2
Flexural modulus	1500 MPa	ISO 178
Charpy impact strength, 23°C	>80 kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, 23°C	5.5 kJ/m <sup>2</sup>	ISO 179/1eA

### Thermal properties

Vicat softening temperature, 50°C/h 50N	65 °C	ISO 306
---	-------	---------

### Flammability

Burning Behav. at 1.5mm nom. thickn.	HB class	IEC 60695-11-10
Burning Behav. at thickness h	HB class	IEC 60695-11-10
Thickness tested	3.2 mm	IEC 60695-11-10

### Physical/Other properties

Density	970 kg/m <sup>3</sup>	ISO 1183
---------	-----------------------	----------

### Characteristics

Processing	Injection Moulding
Additives	Mineral Filler
Special characteristics	U.V. stabilised or stable to weather

### Additional information

Processing Notes

### Storage

This product should be stored in a covered facility and kept away from moisture and heat.