

---

**POLIFOR® C10 T/20 UV NERO - PP**


---

**Description**


---

Polypropylene, copolymer, 20% mineral filled, UV stabilised

Physical properties	Value	Unit	Test Standard
Density	1050	kg/m <sup>3</sup>	ISO 1183
Melt flow rate, MFR	8	g/10min	ISO 1133
MFR temperature	230	°C	ISO 1133
MFR load	2.16	kg	ISO 1133

Mechanical properties	Value	Unit	Test Standard
Tensile modulus	1900	MPa	ISO 527-2/1A
Tensile stress at yield, 50mm/min	22	MPa	ISO 527-2/1A
Tensile strain at break, 50mm/min	>20	%	ISO 527-2/1A
Flexural modulus, 23°C	1900	MPa	ISO 178
Charpy impact strength, 23°C	80	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, 23°C	4.2	kJ/m <sup>2</sup>	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
Vicat softening temperature, 50°C/h 50N	70	°C	ISO 306

**Typical injection moulding processing conditions**


---

Pre Drying	Value	Unit	Test Standard
Drying time	2 - 3	h	-
Drying temperature	80 - 100	°C	-
Temperature	Value	Unit	Test Standard
Zone1 temperature	190 - 210	°C	-
Zone2 temperature	210 - 230	°C	-
Zone3 temperature	220 - 240	°C	-
Nozzle temperature	230 - 250	°C	-
Mold temperature	30 - 60	°C	-

**Other text information**


---

**Longer pre-drying times/storage**


---

This product should be stored in a covered facility and kept away from moisture and heat.

**Characteristics**


---

Special Characteristics	Processing
UV resistant	Injection molding

**Product Categories**


---

Mineral reinforced