

---

**POLIFOR C12 TE/20 NEGRO 900 X1 - PP**


---

<b>Physical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1030</b>	kg/m <sup>3</sup>	ISO 1183
Melt flow rate, MFR	<b>10</b>	g/10min	ISO 1133
MFR temperature	<b>230</b>	°C	ISO 1133
MFR load	<b>2.16</b>	kg	ISO 1133
<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Flexural modulus, 23°C	<b>1600</b>	MPa	ISO 178
Izod impact notched, 23°C	<b>7</b>	kJ/m <sup>2</sup>	ISO 180/1A
<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Vicat softening temperature, 50°C/h 50N	<b>70</b>	°C	ISO 306