

---

**POLIFOR C40 UV NEGRO 900 - PP**


---

<b>Physical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>900</b>	kg/m <sup>3</sup>	ISO 1183
Melt flow rate, MFR	<b>42</b>	g/10min	ISO 1133
MFR temperature	<b>230</b>	°C	ISO 1133
MFR load	<b>2.16</b>	kg	ISO 1133
<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Tensile stress at yield, 50mm/min	<b>22</b>	MPa	ISO 527-2/1A
Tensile strain at break, 50mm/min	<b>&gt;20</b>	%	ISO 527-2/1A
Flexural modulus, 23°C	<b>1150</b>	MPa	ISO 178
Izod impact notched, 23°C	<b>6</b>	kJ/m <sup>2</sup>	ISO 180/1A
<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Vicat softening temperature, 50°C/h 50N	<b>70</b>	°C	ISO 306
Flammability @1.6mm nom. thickn.	<b>HB</b>	class	UL 94