

POLIFOR® C40 UV

POLIFOR®

Product information

Resin Identification	PP	ISO 1043
Part Marking Code	>PP<	ISO 11469

Rheological properties

Melt mass-flow rate	42 g/10min	ISO 1133
Melt mass-flow rate, Temperature	230 °C	
Melt mass-flow rate, Load	2.16 kg	

Typical mechanical properties

Tensile stress at yield, 50mm/min	22 MPa	ISO 527-1/-2
Tensile strain at break, 50mm/min	20 %	ISO 527-1/-2
Flexural modulus	1150 MPa	ISO 178
Izod notched impact strength, 23°C	6 kJ/m ²	ISO 180/1A

Thermal properties

Vicat softening temperature, 50°C/h 50N	70 °C	ISO 306
---	-------	---------

Flammability

Burning Behav. at 1.5mm nom. thickn.	HB class	IEC 60695-11-10
Burning Behav. at thickness h	HB class	IEC 60695-11-10
Thickness tested	3.2 mm	IEC 60695-11-10

Physical/Other properties

Density	900 kg/m ³	ISO 1183
---------	-----------------------	----------