

---

**POLIFOR® CL6 GF/30 UV NERO - PP**


---

**Description**


---

Polypropylene, copolymer, 30% glass fiber reinforced, chemically coupled, UV stabilised, low flow.

Physical properties	Value	Unit	Test Standard
Density	1120	kg/m <sup>3</sup>	ISO 1183
Melt flow rate, MFR	3	g/10min	ISO 1133
MFR temperature	230	°C	ISO 1133
MFR load	2.16	kg	ISO 1133

Mechanical properties	Value	Unit	Test Standard
Tensile modulus	6300	MPa	ISO 527-2/1A
Tensile stress at break, 5mm/min	70	MPa	ISO 527-2/1A
Tensile strain at break, 5mm/min	3.5	%	ISO 527-2/1A
Flexural modulus, 23°C	6200	MPa	ISO 178
Charpy notched impact strength, 23°C	14	kJ/m <sup>2</sup>	ISO 179/1eA
Izod impact notched, 23°C	16	kJ/m <sup>2</sup>	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
DTUL at 1.8 MPa	140	°C	ISO 75-1, -2
Flammability @1.6mm nom. thickn.	HB	class	UL 94

**Typical injection moulding processing conditions**


---

Pre Drying	Value	Unit	Test Standard
Drying time	2 - 3	h	-
Drying temperature	80 - 100	°C	-
Temperature	Value	Unit	Test Standard
Zone1 temperature	200 - 220	°C	-
Zone2 temperature	220 - 240	°C	-
Zone3 temperature	240 - 260	°C	-
Nozzle temperature	240 - 260	°C	-
Mold temperature	50 - 80	°C	-

**Characteristics**


---

Special Characteristics	Processing
UV resistant	Injection molding

**Product Categories**


---

Glass reinforced