

---

**POLIFOR E28 UV NEGRO 900 - PP**


---

<b>Physical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>910</b>	kg/m <sup>3</sup>	ISO 1183
Melt flow rate, MFR	<b>32</b>	g/10min	ISO 1133
MFR temperature	<b>230</b>	°C	ISO 1133
MFR load	<b>2.16</b>	kg	ISO 1133

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Tensile stress at yield, 50mm/min	<b>16</b>	MPa	ISO 527-2/1A
Tensile stress at break, 50mm/min	<b>15</b>	MPa	ISO 527-2/1A
Tensile strain at break, 50mm/min	<b>&gt;300</b>	%	ISO 527-2/1A
Flexural modulus, 23°C	<b>800</b>	MPa	ISO 178
Izod impact notched, 23°C	<b>30</b>	kJ/m <sup>2</sup>	ISO 180/1A

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Vicat softening temperature, 50°C/h 50N	<b>50</b>	°C	ISO 306