

TALCOPRENE® 340TL

TALCOPRENE®

Polypropylene, homopolymer, mineral filled, high heat stabilization.

Product information

Resin Identification	PP-T37	ISO 1043
Part Marking Code	>PP-T37<	ISO 11469

Rheological properties

Melt mass-flow rate	4.5 g/10min	ISO 1133
Melt mass-flow rate, Temperature	230 °C	
Melt mass-flow rate, Load	2.16 kg	

Typical mechanical properties

Tensile modulus	3400 MPa	ISO 527-1/-2
Tensile stress at yield, 50mm/min	29 MPa	ISO 527-1/-2
Tensile strain at yield, 50mm/min	3 %	ISO 527-1/-2
Tensile strain at break, 50mm/min	12 %	ISO 527-1/-2
Flexural modulus	3500 MPa	ISO 178
Flexural strength	45 MPa	ISO 178
Charpy impact strength, 23°C	33 kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 23°C	2.6 kJ/m ²	ISO 179/1eA
Poisson's ratio	0.37 ^[C]	

[C]: Calculated

Thermal properties

Temperature of deflection under load, 1.8 MPa	72 °C	ISO 75-1/-2
Vicat softening temperature, 50°C/h 50N	95 °C	ISO 306

Flammability

Burning Behav. at 1.5mm nom. thickn.	HB class	IEC 60695-11-10
Burning Behav. at thickness h	HB class	IEC 60695-11-10
Thickness tested	3.2 mm	IEC 60695-11-10

Physical/Other properties

Density	1240 kg/m ³	ISO 1183
---------	------------------------	----------

Characteristics

Processing	Injection Moulding
Additives	Mineral Filler
Special characteristics	Heat stabilised or stable to heat

Additional information

Processing Notes

Storage

This product should be stored in a covered facility and kept away from moisture and heat.