

**TALCOPRENE® C1005MF EL - PP**

Experimental Grade. Please contact your Celanese representative for further information.

**Description**

Polypropylene, copolymer, elastomer modified, mineral filled, UV stabilised.

**Physical properties**

ISO	Value	Unit	Test Standard
Density	930	kg/m <sup>3</sup>	ISO 1183
Melt flow rate, MFR	15	g/10min	ISO 1133
MFR temperature	230	°C	ISO 1133
MFR load	2.16	kg	ISO 1133

**Mechanical properties**

ISO	Value	Unit	Test Standard
Tensile modulus	1300	MPa	ISO 527-2/1A
Tensile stress at yield, 50mm/min	16	MPa	ISO 527-2/1A
Tensile nominal strain at break, 50mm/min	>350	%	ISO 527-2/1A
Flexural modulus, 23°C	1200	MPa	ISO 178
Flexural strength, 23°C	20	MPa	ISO 178
Charpy impact strength, 23°C	NB	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, 23°C	32	kJ/m <sup>2</sup>	ISO 179/1eA
Izod impact notched, 23°C	30	kJ/m <sup>2</sup>	ISO 180/1A

**Thermal properties**

ISO	Value	Unit	Test Standard
Melting point, peak	164	°C	ISO 3146
Flammability @1.6mm nom. thickn.	HB	class	UL 94

**Typical injection moulding processing conditions**
**Pre Drying**

	DryTime	DryTemp
max	3 h	100 °C
min	2 h	80 °C

**Temperature**

	CavTemp	MTemp	Z3Temp	Z2Temp	Z1Temp
max	60 °C	250 °C	240 °C	230 °C	210 °C
min	30 °C	230 °C	220 °C	210 °C	190 °C

**Other text information**
**Longer pre-drying times/storage**

This product should be stored in a covered facility and kept away from moisture and heat.

**Characteristics**
**Special Characteristics**

Specialty appearance, UV resistant

**Processing**

Injection molding

**Product Categories**

Impact modified