

# TECNOPRENE® 3K6ELV0

## TECNOPRENE®

PP copolymer, 30% glass fiber reinforced, chemical bonded, elastomer modified, V0

### Product information

Resin Identification	PP-GF30	ISO 1043
Part Marking Code	>PP-GF30<	ISO 11469

### Rheological properties

Melt mass-flow rate	3.4 g/10min	ISO 1133
Melt mass-flow rate, Temperature	230 °C	
Melt mass-flow rate, Load	2.16 kg	

### Typical mechanical properties

Tensile modulus	6700 MPa	ISO 527-1/-2
Tensile stress at break, 5mm/min	54 MPa	ISO 527-1/-2
Tensile strain at break, 5mm/min	3 %	ISO 527-1/-2
Flexural modulus	6700 MPa	ISO 178
Flexural stress at 3.5%	88 MPa	ISO 178
Charpy notched impact strength, 23°C	20 kJ/m <sup>2</sup>	ISO 179/1eA
Poisson's ratio	0.35 <sup>[C]</sup>	

[C]: Calculated

### Thermal properties

Temperature of deflection under load, 1.8 MPa	115 °C	ISO 75-1/-2
---	--------	-------------

### Flammability

Burning Behav. at 1.5mm nom. thickn.	V-0 class	IEC 60695-11-10
Thickness tested	1.5 mm	IEC 60695-11-10
UL recognition	yes	UL 94
Burning Behav. at thickness h	V-0 class	IEC 60695-11-10
Thickness tested	2.5 mm	IEC 60695-11-10
UL recognition	yes	UL 94
Burning Behav. 5V at thickness h	5VA class	IEC 60695-11-20
Thickness tested	2.5 mm	IEC 60695-11-20
UL recognition	yes	UL 94

### Physical/Other properties

Density	1460 kg/m <sup>3</sup>	ISO 1183
---------	------------------------	----------

### Additional information

Processing Notes

### Storage

This product should be stored in a covered facility and kept away from moisture and heat.