

TECNOPRENE® A60K2

TECNOPRENE®

Polypropylene, homopolymer, 10% glass fiber reinforced, chemically coupled.

Product information

Resin Identification	PP-GF10	ISO 1043
Part Marking Code	>PP-GF10<	ISO 11469

Rheological properties

Melt mass-flow rate	3.8 g/10min	ISO 1133
Melt mass-flow rate, Temperature	230 °C	
Melt mass-flow rate, Load	2.16 kg	

Typical mechanical properties

Tensile modulus	3000 MPa	ISO 527-1/-2
Tensile stress at break, 5mm/min	50 MPa	ISO 527-1/-2
Tensile strain at break, 5mm/min	4.5 %	ISO 527-1/-2
Flexural modulus	2800 MPa	ISO 178
Flexural strength	80 MPa	ISO 178
Charpy notched impact strength, 23°C	6.5 kJ/m ²	ISO 179/1eA
Izod notched impact strength, 23°C	7 kJ/m ²	ISO 180/1A
Poisson's ratio	0.37 ^[C]	

[C]: Calculated

Thermal properties

Temperature of deflection under load, 1.8 MPa	120 °C	ISO 75-1/-2
---	--------	-------------

Flammability

Burning Behav. at 1.5mm nom. thickn.	HB class	IEC 60695-11-10
Burning Behav. at thickness h	HB class	IEC 60695-11-10
Thickness tested	3.2 mm	IEC 60695-11-10

Physical/Other properties

Density	970 kg/m ³	ISO 1183
---------	-----------------------	----------

Characteristics

Processing	Injection Moulding
------------	--------------------

Additional information

Processing Notes

Storage

This product should be stored in a covered facility and kept away from moisture and heat.