

---

**TECNOPRENE A60K6 ATX NEGRO 900 - PP**

---

<b>Physical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1120</b>	kg/m <sup>3</sup>	ISO 1183
Melt flow rate, MFR	<b>3</b>	g/10min	ISO 1133
MFR temperature	<b>230</b>	°C	ISO 1133
MFR load	<b>2.16</b>	kg	ISO 1133
<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Tensile stress at break, 5mm/min	<b>82</b>	MPa	ISO 527-2/1A
Flexural modulus, 23°C	<b>5800</b>	MPa	ISO 178
Charpy impact strength, 23°C	<b>35</b>	kJ/m <sup>2</sup>	ISO 179/1eU
Izod impact notched, 23°C	<b>13</b>	kJ/m <sup>2</sup>	ISO 180/1A
<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
DTUL at 1.8 MPa	<b>145</b>	°C	ISO 75-1, -2