

---

**TECNOPRENE® AK6/D NAT003 - PP**


---

**Description**


---

Polypropylene, homopolymer, 30% glass fiber reinforced, chemically coupled, detergent resistant.

Physical properties	Value	Unit	Test Standard
Density	1120	kg/m <sup>3</sup>	ISO 1183
Melt flow rate, MFR	3.2	g/10min	ISO 1133
MFR temperature	230	°C	ISO 1133
MFR load	2.16	kg	ISO 1133

Mechanical properties	Value	Unit	Test Standard
Tensile modulus	6500	MPa	ISO 527-2/1A
Tensile stress at break, 5mm/min	80	MPa	ISO 527-2/1A
Tensile strain at break, 5mm/min	3.5	%	ISO 527-2/1A
Flexural modulus, 23°C	5900	MPa	ISO 178
Flexural strength, 23°C	130	MPa	ISO 178
Charpy notched impact strength, 23°C	11.5	kJ/m <sup>2</sup>	ISO 179/1eA
Izod impact notched, 23°C	12.5	kJ/m <sup>2</sup>	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
DTUL at 1.8 MPa	145	°C	ISO 75-1, -2
Flammability at thickness h	HB	class	UL 94
thickness tested (h)	1.50	mm	UL 94
UL recognition (h)	UL	-	UL 94

**Typical injection moulding processing conditions**


---

Pre Drying	Value	Unit	Test Standard
Drying time	2 - 3	h	-
Drying temperature	80 - 100	°C	-
Temperature	Value	Unit	Test Standard
Zone1 temperature	200 - 220	°C	-
Zone2 temperature	220 - 240	°C	-
Zone3 temperature	240 - 260	°C	-
Nozzle temperature	240 - 260	°C	-
Mold temperature	50 - 80	°C	-

**Other text information**


---

**Longer pre-drying times/storage**


---

This product should be stored in a covered facility and kept away from moisture and heat.

**Characteristics**


---

**Product Categories**

Glass reinforced

**Processing**

Injection molding