

TECNOPRENE® FK8T1 LE

TECNOPRENE®

Product information

Resin Identification	PP-GF40	ISO 1043
Part Marking Code	>PP-GF40<	ISO 11469

Rheological properties

Melt mass-flow rate	5 g/10min	ISO 1133
Melt mass-flow rate, Temperature	230 °C	
Melt mass-flow rate, Load	2.16 kg	

Typical mechanical properties

Tensile modulus	9000 MPa	ISO 527-1/-2
Tensile stress at break, 5mm/min	100 MPa	ISO 527-1/-2
Tensile strain at break, 5mm/min	3 %	ISO 527-1/-2
Flexural modulus	8400 MPa	ISO 178
Flexural strength	160 MPa	ISO 178
Charpy notched impact strength, 23°C	14 kJ/m ²	ISO 179/1eA
Izod notched impact strength, 23°C	13 kJ/m ²	ISO 180/1A
Poisson's ratio	0.34 ^[C]	

[C]: Calculated

Thermal properties

Temperature of deflection under load, 1.8 MPa	149 °C	ISO 75-1/-2
---	--------	-------------

Flammability

Burning Behav. at thickness h	HB class	IEC 60695-11-10
Thickness tested	3.2 mm	IEC 60695-11-10
FMVSS Class	B	ISO 3795 (FMVSS 302)
Burning rate, Thickness 1 mm	59.5 mm/min	ISO 3795 (FMVSS 302)

Physical/Other properties

Density	1210 kg/m ³	ISO 1183
---------	------------------------	----------