

## TECNOPRENE® FKM22UA NAT005 - PP

### Description

Polypropylene, homopolymer, 10% talc filled, 10% glass fiber reinforced, chemically coupled, UV stabilised, with antistatic additive

Physical properties	Value	Unit	Test Standard
Density	1040	kg/m <sup>3</sup>	ISO 1183
Melt flow rate, MFR	10	g/10min	ISO 1133
MFR temperature	230	°C	ISO 1133
MFR load	2.16	kg	ISO 1133

Mechanical properties	Value	Unit	Test Standard
Tensile modulus	3700	MPa	ISO 527-2/1A
Tensile stress at break, 5mm/min	50	MPa	ISO 527-2/1A
Tensile strain at break, 5mm/min	3.5	%	ISO 527-2/1A
Flexural modulus, 23°C	3300	MPa	ISO 178
Flexural strength, 23°C	85	MPa	ISO 178
Charpy notched impact strength, 23°C	5	kJ/m <sup>2</sup>	ISO 179/1eA
Izod impact notched, 23°C	5.5	kJ/m <sup>2</sup>	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
DTUL at 1.8 MPa	128	°C	ISO 75-1, -2
Flammability @1.6mm nom. thickn.	HB	class	UL 94

### Typical injection moulding processing conditions

Pre Drying	Value	Unit	Test Standard
Drying time	2 - 3	h	-
Drying temperature	80 - 100	°C	-
Temperature	Value	Unit	Test Standard
Zone1 temperature	200 - 220	°C	-
Zone2 temperature	220 - 240	°C	-
Zone3 temperature	240 - 260	°C	-
Mold temperature	50 - 80	°C	-

### Other text information

#### Longer pre-drying times/storage

This product should be stored in a covered facility and kept away from moisture and heat.

### Characteristics

#### Special Characteristics

Anti-static, UV resistant

#### Processing

Injection molding

#### Product Categories

Mineral/Glass reinforced