

**TECNOPRENE® VK6T1LE NERO900 - PP**

Experimental Grade. Please contact your Celanese representative for further information.

**Description**

Polypropylene, homopolymer, 30% glass fiber reinforced, chemically coupled, low emission, high flow, high heat stabilisation.

Physical properties	Value	Unit	Test Standard
Density	1130	kg/m <sup>3</sup>	ISO 1183
Melt flow rate, MFR	13	g/10min	ISO 1133
MFR temperature	230	°C	ISO 1133
MFR load	2.16	kg	ISO 1133

Mechanical properties	Value	Unit	Test Standard
Tensile modulus	7200	MPa	ISO 527-2/1A
Tensile stress at break, 5mm/min	98	MPa	ISO 527-2/1A
Tensile strain at break, 5mm/min	2.9	%	ISO 527-2/1A
Flexural modulus, 23°C	6500	MPa	ISO 178
Flexural strength, 23°C	150	MPa	ISO 178
Charpy impact strength, 23°C	>60	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, 23°C	11	kJ/m <sup>2</sup>	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
DTUL at 1.8 MPa	144	°C	ISO 75-1, -2
Flammability @1.6mm nom. thickn.	HB	class	UL 94

**Typical injection moulding processing conditions**

Pre Drying	Value	Unit	Test Standard
Drying time	2 - 3	h	-
Drying temperature	80 - 100	°C	-
Temperature	Value	Unit	Test Standard
Zone1 temperature	200 - 220	°C	-
Zone2 temperature	220 - 240	°C	-
Zone3 temperature	240 - 260	°C	-
Nozzle temperature	240 - 260	°C	-
Mold temperature	50 - 80	°C	-

**Other text information**
**Longer pre-drying times/storage**

This product should be stored in a covered facility and kept away from moisture and heat.

**Characteristics**

Special Characteristics	Processing
High flow	Injection molding

**Product Categories**

Low emission, Glass reinforced