

TECNOPRENE® VKB35HCTR

TECNOPRENE®

Polypropylene, homopolymer, 25% glass beads and 15% glass fiber reinforced, chemically coupled, heat and copper contact stabilized

Product information

Resin Identification	PP-(GF+GB)40	ISO 1043
Part Marking Code	>PP-(GF+GB)40<	ISO 11469

Rheological properties

Melt mass-flow rate	15 g/10min	ISO 1133
Melt mass-flow rate, Temperature	230 °C	
Melt mass-flow rate, Load	2.16 kg	

Typical mechanical properties

Tensile modulus	5500 MPa	ISO 527-1/-2
Tensile stress at break, 5mm/min	66 MPa	ISO 527-1/-2
Tensile strain at break, 5mm/min	2.8 %	ISO 527-1/-2
Flexural modulus	5400 MPa	ISO 178
Flexural strength	100 MPa	ISO 178
Charpy impact strength, 23°C	30 kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 23°C	5.5 kJ/m ²	ISO 179/1eA
Izod notched impact strength, 23°C	6 kJ/m ²	ISO 180/1A
Poisson's ratio	0.35 ^[C]	

[C]: Calculated

Thermal properties

Temperature of deflection under load, 1.8 MPa	142 °C	ISO 75-1/-2
---	--------	-------------

Flammability

Burning Behav. at 1.5mm nom. thickn.	HB class	IEC 60695-11-10
Burning Behav. at thickness h	HB class	IEC 60695-11-10
Thickness tested	3.2 mm	IEC 60695-11-10

Physical/Other properties

Density	1220 kg/m ³	ISO 1183
---------	------------------------	----------

Characteristics

Processing	Injection Moulding
Additives	Metal deactivator
Special characteristics	Heat stabilised or stable to heat

Additional information

Processing Notes

Storage

This product should be stored in a covered facility and kept away from moisture and heat.

TECNOPRENE® VKB35HCTR

TECNOPRENE®

Automotive

OEM
VW Group

STANDARD
VW 44045