

# TECNOPRENE® VKM42LP

## TECNOPRENE®

Polypropylene, homopolymer, 10% talc filled, 20% glass fiber reinforced, chemically coupled, laser printable.

### Product information

Resin Identification	PP-(GF+T)30	ISO 1043
Part Marking Code	>PP-(GF+T)30<	ISO 11469

### Rheological properties

Melt mass-flow rate	15 g/10min	ISO 1133
Melt mass-flow rate, Temperature	230 °C	
Melt mass-flow rate, Load	2.16 kg	

### Typical mechanical properties

Tensile modulus	5700 MPa	ISO 527-1/-2
Tensile stress at break, 5mm/min	68 MPa	ISO 527-1/-2
Tensile strain at break, 5mm/min	3 %	ISO 527-1/-2
Flexural modulus	5500 MPa	ISO 178
Flexural strength	120 MPa	ISO 178
Charpy notched impact strength, 23 °C	7 kJ/m <sup>2</sup>	ISO 179/1eA
Izod notched impact strength, 23 °C	7 kJ/m <sup>2</sup>	ISO 180/1A
Poisson's ratio	0.35 <sup>[C]</sup>	

[C]: Calculated

### Thermal properties

Temperature of deflection under load, 1.8 MPa	145 °C	ISO 75-1/-2
---	--------	-------------

### Flammability

Burning Behav. at 1.5mm nom. thickn.	HB class	IEC 60695-11-10
Burning Behav. at thickness h	HB class	IEC 60695-11-10
Thickness tested	3.2 mm	IEC 60695-11-10

### Physical/Other properties

Density	1130 kg/m <sup>3</sup>	ISO 1183
---------	------------------------	----------

### Characteristics

Processing	Injection Moulding
Special characteristics	Laser Markable

### Additional information

Processing Notes

### Storage

This product should be stored in a covered facility and kept away from moisture and heat.