

CELSTRAN® +PP-GF40-01 | PP | Glass Reinforced

Pressure:

	Inj press	Hold press	Back pressure
min (bar)	600	400	0
max (bar)	1200	800	30

Speed:

Injection speed: slow

Screw speed

Screw diameter (mm)	16	25	40	55	75
Screw speed (RPM)	-	-	50	35	25

Special Info:

Assessment of mechanical values using an injection molding machine with dedicated screw. Implementation: Feb. 2010