

CELSTRAN® PPS-GF40-01 AD3002 BLACK

CELSTRAN® Long Fibre

40% long strand fiber glass reinforced polyphenylene sulfide

Product information

Resin Identification	PPS-LGF40	ISO 1043
Part Marking Code	>PPS-LGF40<	ISO 11469

Typical mechanical properties

Tensile modulus	15900 MPa	ISO 527-1/-2
Tensile stress at break, 5mm/min	155 MPa	ISO 527-1/-2
Tensile strain at break, 5mm/min	1.1 %	ISO 527-1/-2
Flexural modulus	14900 MPa	ISO 178
Flexural strength	250 MPa	ISO 178
Charpy notched impact strength, 23°C	22 kJ/m ²	ISO 179/1eA
Izod notched impact strength, 23°C	34 kJ/m ²	ISO 180/1A
Izod impact strength, -40°C	34.2 kJ/m ²	ISO 180/1U
Poisson's ratio	0.33 ^[C]	

[C]: Calculated

Physical/Other properties

Density	1620 kg/m ³	ISO 1183
---------	------------------------	----------

Characteristics

Processing	Injection Moulding
Delivery form	Pellets
Special characteristics	Heat stabilised or stable to heat

Additional information

Processing Notes

Pre-Drying

FORTRON should in principle be predried. Because of the necessary low maximum residual moisture content the use of dry air dryers is recommended. The dew point should be =< -30°C. The time between drying and processing should be as short as possible.

Storage

For subsequent storage the material should be stored dry in the dryer until processed (<= 60 h).