

CELSTRAN® PPS-GF50-01 AD3002 Black

50% long strand glass fiber reinforced polyphenylene sulfide. UL-V0 flame retardant.
50% long strand glass fiber reinforced polyphenylene sulfide

Typical mechanical properties

Tensile Modulus	19000 MPa	ISO 527-1/-2
Stress at break, 5mm/min	165 MPa	ISO 527-1/-2
Strain at break, 5mm/min	1 %	ISO 527-1/-2
Flexural Modulus	18600 MPa	ISO 178
Flexural Strength	280 MPa	ISO 178
Charpy notched impact strength, 23°C	28 kJ/m ²	ISO 179/1eA

Thermal properties

Temp. of deflection under load, 1.8 MPa	282 °C	ISO 75-1/-2
-----------------------------------------	--------	-------------

Other properties

Density	1720 kg/m ³	ISO 1183
---------	------------------------	----------

Injection

Drying Temperature	130 - 140 °C
Drying Time, Dehumidified Dryer	3 - 4 h
Processing Moisture Content	0.02 %
Max. mould temperature	140 - 160 °C

Processing Texts

Pre-drying FORTRON should in principle be predried. Because of the necessary low maximum residual moisture content the use of dry air dryers is recommended. The dew point should be =< -30°C. The time between drying and processing should be as short as possible.

Longer pre-drying times/storage For subsequent storage the material should be stored dry in the dryer until processed (<= 60 h).