

FORTRON[®] 4332L6

Polyphenylene sulfide

Fortron 4332L6 is a glass fiber/mineral filled injection molding grade, which is intended for applications requiring improved tensile and flexural properties, when compared to other GF/MIN reinforced PPS grades. The recommended processing parameters are similar to the standard grades.

Product information

Resin Identification	PPS-(GF+MD)6 5	ISO 1043
Part Marking Code	>PPS-(GF+MD)65<	ISO 11469

Rheological properties

Moulding shrinkage range, parallel	0.2 - 0.6 %	ISO 294-4, 2577
Moulding shrinkage range, normal	0.3 - 0.7 %	ISO 294-4, 2577

Typical mechanical properties

Tensile modulus	22500 MPa	ISO 527-1/-2
Tensile stress at break, 5mm/min	160 MPa	ISO 527-1/-2
Tensile strain at break, 5mm/min	1.2 %	ISO 527-1/-2
Flexural modulus	21000 MPa	ISO 178
Flexural strength	260 MPa	ISO 178
Charpy impact strength, 23°C	30 kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 23°C	6.5 kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	6.1 kJ/m ²	ISO 179/1eA
Poisson's ratio	0.309	

Thermal properties

Melting temperature, 10°C/min	280 °C	ISO 11357-1/-3
Glass transition temperature, 10°C/min	90 °C	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	270 °C	ISO 75-1/-2
Temperature of deflection under load, 8 MPa	220 °C	ISO 75-1/-2
Coefficient of linear thermal expansion (CLTE), parallel	12 E-6/K	ISO 11359-1/-2
Coefficient of linear thermal expansion (CLTE), normal	45 E-6/K	ISO 11359-1/-2
Thermal conductivity, flow	0.63 ^[OT] W/(m K)	ISO 22007-2
Thermal conductivity, crossflow	0.58 ^[OT] W/(m K)	ISO 22007-2
Thermal conductivity, through plane	0.6 ^[OT] W/(m K)	ISO 22007-2
Effective thermal diffusivity, flow	3.6E-7 ^[OT] m ² /s	ISO 22007-4
Effective thermal diffusivity, crossflow	3.3E-7 ^[OT] m ² /s	ISO 22007-4
Effective thermal diffusivity, through plane	3.4E-7 ^[OT] m ² /s	ISO 22007-4
Specific heat capacity of melt	890 ^[OT] J/(kg K)	ISO 22007-4

[OT]: One time tested

Flammability

Burning Behav. at 1.5mm nom. thickn.	V-0 class	IEC 60695-11-10
FMVSS Class	SE	ISO 3795 (FMVSS 302)
Burning rate, Thickness 1 mm	mm/min	ISO 3795 (FMVSS 302)

FORTRON® 4332L6

Polyphenylene sulfide

Physical/Other properties

Water absorption, 2mm	0.02 %	Sim. to ISO 62
Density	1950 kg/m ³	ISO 1183

Injection

Drying Recommended	yes
Drying Temperature	130 °C
Drying Time, Dehumidified Dryer	2 - 4 h
Processing Moisture Content	≤0.02 %
Melt Temperature Optimum	330 °C
Min. melt temperature	310 °C
Max. melt temperature	340 °C
Screw tangential speed	0.2 - 0.3 m/s
Mold Temperature Optimum	150 °C
Min. mould temperature	140 °C
Max. mould temperature	160 °C
Hold pressure range	30 - 70 MPa
Back pressure	3 MPa
Ejection temperature	225 °C

Characteristics

Processing	Injection Moulding
Special characteristics	Flame retardant, High Flow, Improved creep

Additional information

Injection molding

Preprocessing

Predrying in a dehumidified air dryer at 130 - 140 degC/3-4 hours is recommended.

Processing

On injection molding machines with 15-25 D long three-section screws, as are usual in the trade, the FORTRON is processable. A shut-off nozzle is preferred to a free-flow nozzle.

Melt temperature 320-340 degC
Mold wall temperature at least 140 degC

A medium injection rate is normally preferred. All mold cavities must be effectively vented.

Postprocessing

Tool temperature of at least 135 degC is recommended for parts to achieve maximum crystallizable potential.


FORTRON® 4332L6

Polyphenylene sulfide

Automotive

OEM	STANDARD	ADDITIONAL INFORMATION
BMW	GS93016	SD3002 Black
General Motors	GMW17519P-PPS-(GF45-MD20)	Natural
General Motors	GMW17519P-PPS-(GF45-MD20)	Black

Stress-strain



FORTRON® 4332L6

Polyphenylene sulfide

Secant modulus-strain

